

POLYFLON PTFE FINE POWDER



Technical information

12/2018

POLYFLON PTFE F-205

Fine Powder for Paste Extrusion

POLYFLON PTFE F-205 is a fine powder resin for paste extrusion. It has been specifically designed for the manufacture of thin wall tubing and wire coating applications requiring good color, clarity, thermal stability and stress crack resistance.

Typical properties

• • • •			
Average Particles size	μm	400 - 650	ASTM D 4895
Bulk Density	g/l	400 - 600	ASTM D 4895
Specific Gravity		2,16 - 2,20	ASTM D 4895
Melting Point	°C	322 - 328	ASTM D 4895
Extrusion Pressure (at RR 1500)	MPa	63 - 83	Daikin Method
Tensile Strength	MPa	>25	ASTM D 4895
Elongation	%	>350	ASTM D 4895

Note: Typical properties are not suitable for specification purpose

Typical applications

Small thin wall tubing

Heat srinkable tubing

· Wire coating applications

Packaging

POLYFLON PTFE Fine Powders are packaged in 25kg plastic drums.

Important Notice

The information contained herein is based on technical data and tests we believe to be reliable and is intended for use by persons having technical knowledge and skill, solely at their own discretion and risk. Since conditions of use are outside of our control, we assume no responsibility for results obtained or damages incurred through application of the data given. The publication of the information herein shall not be understood as permission or recommendation for the use of our fluorocarbon compounds in violation of any patent or otherwise. We only warrant that the product conforms to description and specification, and our only obligation shall be to replace goods shown to be defective or refund the original purchase price thereof.

USE OF PRODUCT: The product is for the industrial use only. We do not guarantee the safety in case the product is used for the other purposes. When using the product for health-care application or for food/feed application, consult us in advance.

MEDICAL USE:These products are not specifically designed or manufactured for use in implantable medical and/or dental devices. They have not been tested for such applications and will only be sold for such use pursuant to contract containing specific terms and conditions required by us.

www.daikin.com

Daikin Chemical Europe GmbH

Am Wehrhahn 50 40211 Düsseldorf Germany

Phone: +49-211-1792250 Fax: +49-211-1640732 www.daikinchem.de

Daikin Industries, Ltd.

Umeda Center Building 2-4-12 Nakasaki-Nishi, Kita-ku Osaka 530-8323, Japan Phone: +81-6-6374-9355 Fax: +81-6-6374-4281

Daikin America, Inc.

20 Olympic Drive Orangeburg, NY 10962 USA

Phone: +1-845-365-9500 Fax: +1-845-365-9515 www.daikin-america.com