

POLYFLON PTFE F-131

Fine Powder for Paste Extrusion

POLYFLON PTFE F-131 is a high molecular weight polytetrafluoroethylene fine powder resin for paste extrusion. F-131 has been specifically designed for the manufacture of unsintered tapes, sintered tapes and porous applications at low reduction ratios. It has high thermal stability and high stretch ratio capability.

Typical properties

Average Particles size	µm	400 ~ 650	ASTM D 4895
Bulk Density	g/l	> 400	ASTM D 4895
Specific Gravity		2,145 ~ 2,155	ASTM D 4895
Melting Point	°C	326 ~ 328	ASTM D 4895
Extrusion Pressure (at RR 36)	MPa	13,0 ~ 22,0	Daikin Method
Tensile Strength	MPa	25 ~ 100	ASTM D 4895
Elongation	%	300 ~ 900	ASTM D 4895

Note: Typical properties are not suitable for specification purpose

Typical applications

- Tapes
- Porous items

Packaging

POLYFLON PTFE Fine Powders are packaged in 25kg plastic drums.

Important Notice

The information contained herein is based on technical data and tests we believe to be reliable and is intended for use by persons having technical knowledge and skill, solely at their own discretion and risk. Since conditions of use are outside of our control, we assume no responsibility for results obtained or damages incurred through application of the data given. The publication of the information herein shall not be understood as permission or recommendation for the use of our fluorocarbon compounds in violation of any patent or otherwise. We only warrant that the product conforms to description and specification, and our only obligation shall be to replace goods shown to be defective or refund the original purchase price thereof.

USE OF PRODUCT: The product is for the industrial use only. We do not guarantee the safety in case the product is used for the other purposes. When using the product for health-care application or for food/feed application, consult us in advance.

MEDICAL USE: These products are not specifically designed or manufactured for use in implantable medical and/or dental devices. They have not been tested for such applications and will only be sold for such use pursuant to contract containing specific terms and conditions required by us.

Daikin Chemical Europe GmbH

Am Wehrhahn 50
40211 Düsseldorf
Germany
Phone: +49-211-1792250
Fax: +49-211-1640732
www.daikinchem.de

Daikin Industries, Ltd.

Umeda Center Building
2-4-12 Nakasaki-Nishi, Kita-ku
Osaka 530-8323, Japan
Phone: +81-6-6374-9355
Fax: +81-6-6374-4281
www.daikin.com

Daikin America, Inc.

20 Olympic Drive
Orangeburg, NY 10962
USA
Phone: +1-845-365-9500
Fax: +1-845-365-9515
www.daikin-america.com