

Unidyne XF-5005

is a fluorine-free, water-based polymer emulsion. It imparts water repellency to e.g. textiles and nonwovens.

Product Features

- Fluorine-free
- 30% solid
- Imparts excellent water repellency to all types of fabric substrates
- Imparts durability to washing and dry cleaning in combination with booster
- Excellent Bundesmann performance
- Excellent process ability

Physical Properties

Appearance	Whitish - light yellow
Charge	weakly cationic
рН	2 - 5
Specific gravity at 25°C	1,0 - 1,1 g/cm³
Solubility	fully miscible with water

Storage / Shelf-life

- XF-5005 should be stored according to the Material Safety Data Sheet
- Avoid freezing
- When stored using the recommended conditions, shelf-life is 18 months after production date

Safety

Before using this product, please read the current Material Safety Data Sheet and the precautionary statement on the product package. Follow all applicable directions.





Application Guide

- Padding process
- pH of the finishing liquor 3-7
- pick-up 30-90%

Standard recipe

Substrate	Cotton
Concentration	10 - 100 g/l XF-5005
Curing conditions	160 - 180° C, 60 - 120 sec., depending on the material*
Substrate	Synthetics
Concentration	40 - 100 g/l XF-5005
Curing conditions	160 - 180° C, 60 - 120 sec., depending on the material*

Bundesmann recipe

Substrate	Synthetics
Concentration	80 - 120 g/l XF-5005 20 - 40 g/l Cross-linker
Curing conditions	160 - 180° C, 60 - 120 sec., depending on the material*

^{*}The lower the curing temperature, the longer the curing time.

Daikin Chemical Europe GmbH

Am Wehrhahn 50 40211 Düsseldorf Germany

Tel.: +49 211 179225-0 Fax: +49 211 179225-39 www.daikinchem.de