



Neoflon®



PFA PELLETS

Technical Information

AP-230ASL

Features

Neoflon PFA AP-230ASL is an anti-static grade suitable for extrusion molding.

Typical properties

Melt Flow Rate	g/10 min	1.0 ~ 2.5	ASTM D-3207
Melting Point (DSC)	°C	295 ~ 300	ASTM D-3207
Tensile Strength	MPa	min 25	ASTM D-3207
Elongation	%	min 300	ASTM D-3207
Specific Gravity	-	2,12 ~ 2,16	ASTM D-3207

Note: Typical properties are not suitable for specification purpose

Typical Applications

- Extrusion molded parts
- Tubing

Packaging

Neoflon PFA pellets are packaged in 25kg bags.

Important Notice

The information contained herein is based on technical data and tests we believe to be reliable and is intended for use by persons having technical knowledge and skill, solely at their own discretion and risk. Since conditions of use are outside of our control, we assume no responsibility for results obtained or damages incurred through application of the data given. The publication of the information herein shall not be understood as permission or recommendation for the use of our fluorocarbon compounds in violation of any patent or otherwise. We only warrant that the product conforms to description and specification, and our only obligation shall be to replace goods shown to be defective or refund the original purchase price thereof.

MEDICAL USE: These products are not specifically designed or manufactured for use in implantable medical and/or dental devices. They have not been tested for such applications and will only be sold for such use pursuant to contract containing specific terms and conditions required by us.

Daikin Chemical Europe GmbH

Immermannstr, 65D
40210 Düsseldorf
Germany
Phone: +49-211-1792250
Fax: +49-211-1640732
www.daikinchem.de

Daikin Industries, LTD. Umeda Center Building

2-4-12 Nakasaki-Nishi, Kita-ku
Osaka 530-8323
Japan
Phone: +81-6-6374-9355
Fax: +81-6-6374-4281
www.daikin.com

Daikin America, INC. 20 Olympic Drive

Orangeburg, NY 10962
U.S.A.
Phone: (845) 365-9500
Toll Free: (800) 365-9570
Fax: (845) 365-9515
www.daikin-america.com