

## POLYFLON PTFE F-302

### Fine Powder for Past Extrusion

POLYFLON PTFE F-302 is a polytetrafluoroethylene fine powder resin for paste extrusion. It has been designed for tube and heavy wall wire insulations processed at low to medium reduction ratios up to 1.200:1.

#### Typical properties

Average Particles size	µm	Approx. 500	ASTM D 4895
Bulk Density	g/l	Approx. 450	ASTM D 4895
Specific Gravity		Approx. 2.15	ASTM D 4895
Melting Point	°C	326 - 328	ASTM D 4895
Extrusion Pressure (at RR 300)	MPa	12.0 ~ 20.0	Daikin Method
Tensile Strength	MPa	> 20	ASTM D 4895
Elongation	%	> 220	ASTM D 4895

**Note: Typical properties are not suitable for specification purpose**

#### Typical applications

- Small and large diameter tubing
- Shrinkable tube
- Heavy wall electric wire

#### Packaging

POLYFLON PTFE Fine Powders are packaged in 25kg plastic drums.

#### Important Notice

The information contained herein is based on technical data and tests we believe to be reliable and is intended for use by persons having technical knowledge and skill, solely at their own discretion and risk. Since conditions of use are outside of our control, we assume no responsibility for results obtained or damages incurred through application of the data given. The publication of the information herein shall not be understood as permission or recommendation for the use of our fluorocarbon compounds in violation of any patent or otherwise. We only warrant that the product conforms to description and specification, and our only obligation shall be to replace goods shown to be defective or refund the original purchase price thereof.

**MEDICAL USE:** These products are not specifically designed or manufactured for use in implantable medical and/or dental devices. They have not been tested for such applications and will only be sold for such use pursuant to contract containing specific terms and conditions required by us.

#### Daikin Chemical Europe GmbH

Am Wehrhahn 50  
40211 Düsseldorf  
Germany  
Phone: +49-211-1792250  
Fax: +49-211-1640732  
www.daikinchem.de

#### Daikin Industries, Ltd.

Umeda Center Building  
2-4-12 Nakasaki-Nishi, Kita-ku  
Osaka 530-8323, Japan  
Phone: +81-6-6374-9355  
Fax: +81-6-6374-4281  
www.daikin.com

#### Daikin America, Inc.

20 Olympic Drive  
Orangeburg, NY 10962  
U.S.A  
Phone: +1-845-365-9500  
Fax: +1-845-365-9515  
www.daikin-america.com